



MOCOM

❖ Alcom® LD/LD2 HTC Processing Guide Injection Molding

Alcom® LD/LD2* HTC are translucent, optically diffuse and unfilled compounds based on High Temperature Copolyesters (HTC).

The special optical properties of Alcom® LD HTC require special attention during pretreatment and processing of the materials, especially with regards to adherence to injection molding parameters, as well as cleanliness and purity of the processing environment. The following processing instructions provide guide values for handling the materials. The information on pretreatment and processing on the technical data sheet of the product used must also always be followed.

Processing environment

As usual when processing thermoplastic molding compounds into optical components, special care must be taken to ensure cleanliness of machines and peripherals. Contamination and dust in drying equipment, pellet feeders, storage containers or other surfaces the pellets come into contact with can lead to defects and impurities in the

finished part. Dust in particular causes cracking and black entrapments in finished parts during subsequent processing. If larger amounts of dust occur during material handling or transport, the use of an additional dust removal system is recommended. Contamination in injection molding units and mold cavities, e.g. due to residues of foreign material, oil or other processing aids, must also be avoided. Before using Alcom® LD HTC, purge the injection molding unit with clear polycarbonate, polystyrene or purging concentrates until no impurities (e.g. specks, streaks, color haze) are visible in the melt cake.

*Hereinafter referred to as "Alcom® LD HTC"

Material handling

Alcom® LD HTC is usually supplied in bags. This helps to avoid contamination of larger granulate quantities during material handling and thus large reject quantities, as would otherwise be possible with octabin, BigBag or silo goods. Store unopened bags dry and protected from light. Opened residual containers must be sealed airtight after opening and checked for increased residual moisture and contamination before processing.

Pretreatment

HTC is a hygroscopic polymer and absorbs moisture from the ambient air which can lead to material damage and surface defects during injection molding. Therefore, pre-drying, preferably in a dry air dryer, is necessary until a residual moisture of 0.03% maximum (Karl Fischer titration) is reached. Ensure the drying equipment is clean and free of dust in order to prevent contamination. The material must be processed immediately and continuously after pre-drying as it absorbs moisture from the ambient air again in the material supply of the injection molding machine. After longer production stops it may be necessary to dry the granules again if they have not been stored airtight.

Processing

Alcom® LD HTC can be processed on all standard injection molding machines with 3-zone screw. Please follow the recommended process conditions given below, as well as the recommendations on the technical data sheet of the product used. In the following, some points are considered which should be given special attention when processing Alcom® LD HTC.


Plasticizing: A screw speed and back pressure set correctly contribute significantly to a homogeneous melt quality. However, both parameters should not be set too high in order to avoid damage to the molding compound due to excessive shear energies. A screw circumferential speed < 0.15 m/s and a specific back pressure between 50-100 bar are recommended.

Nozzle: Open or valve gate nozzles can be used. However, due to their design, valve gate nozzles may cause increased shear and possible zones with increased residence time. Both can lead to component defects due to streaks or black specks. Purging during material changes is also more complex with valve gate nozzles.

Residence time: Excessive residence time can lead to material damage and color deviations (“yellowing”). Make sure the size of the plasticizing unit used matches the shot volume of the injection mold used. The recommended dosing volume is 1-3 times the screw diameter (1-3D). Residence times of the material in the plasticizing should be 6 minutes maximum.

Processing temperatures: The processing temperatures recommended on the technical data sheet must be followed. Temperatures too high can lead to significant color deviations and material degradation. Temperatures too low increase the injection pressure. This leads to excessive shear and increased stresses in the component, up to and including component failure. As a guide for initial sampling it is recommended to start with the mean value of the processing temperatures specified on the technical data sheet. In case of production interruptions residual material in the aggregate should be purged and barrel temperatures should be lowered to 130°C - 150°C. Before re-starting production, the plasticizing unit should be purged with material until no more degraded/discolored melt is being extruded and the melt cake is free of streaks and black specks.

Injection speed and holding pressure: The injection speed should ensure component filling with constant flow front speed. The holding pressure should be between 50% to 70% of the maximum injection pressure. Uneven filling and excessive pressures cause internal stresses in the component, which can lead to warpage and damage to the component. At very high injection pressures (> 1500 bar), the gating system should be checked and adjusted if necessary (e.g. by larger gate diameter).



Injection Mold

Temperature control: Uniform mold surface temperature is mandatory for optimum component quality. The best appearance is met by choosing mold temperatures in the upper range. Special attention must be taken to inserts and sliders in complex molds. We recommend checking the temperature control by measuring the mold surface temperature (e.g. with a contact thermometer). Insufficient or uneven mold temperature control can cause component defects, such as increased warpage.

Gating: The gate should be located in an area of highest wall thickness in order to ensure the optimum effect of the holding pressure to reduce sink marks. The position of the gate should support uniform cavity filling with short flow paths. The type of gate chosen must ensure gentle material processing. Point and tunnel gates can be used but minimum diameter of the gate should not be less than 1.0 mm. Excessive shear stress on the molding compound can lead to color changes under certain circumstances.

Hot runner: The use of hot runner systems for processing Alcom® LD HTC is possible and has been proven for a long time. Care should be taken to a hot runner design without dead angles and with the smallest possible volume to reduce the residence time. At the same time, the hot runner system should introduce as little shear stress as possible to the molding compound. Torpedo tips should be avoided. Hot runner nozzles with valve gates are possible but extend purging time and cause streaks more frequently. Please follow the maximum processing temperatures of the material used in the hot runner system as well.

Surface: Due to the special formulation of Alcom® LD HTC, optimum light diffusion is achieved even on polished surfaces. Structuring is not necessary. In the case of large-area components with (mirror-bright) polished surfaces, demolding problems may occur due to surface adhesion. These can be counteracted by suitable mold coatings. For further information please contact your technical representative.

Use of regrind

Alcom® LD are materials for highest technical and optical requirements with narrow color tolerances. The use of ground production waste (e.g. sprues) is not recommended. Dust, impurities and also the increased thermal load due to re-melting mean that the optical quality of the components cannot be ensured. Please feed production waste into the recycling circuit instead.

Properties

Polymer	HTC
Density (ISO 1183)	1.18 - 1.20 g/cm ³ (see technical datasheet)

Injection molding machine

Screw stroke	Dosing stroke between 1 x D and 3 x D (D = screw diameter)
Screw type	Three-zone screw with L/D-ratio 18:1 to 23:1
Nozzle type	Open or needle valve nozzle
Hopper type	Standard

Pretreatment

Storage	Dry, protected from heat and UV radiation
Dryer	Dry air dryer
Drying time	4 - 6 h
Drying temperature	90 °C
Max. moisture content	< 0.03 %

Processing conditions

Melt temperature	260 - 280 °C (for type-related values please see technical data sheet)
Tool temperature	50 - 70 °C
Coolant	Water
Coolant throughput	A turbulent flow is to be achieved
Screw circumferential speed	50 - 150 mm/s
Back pressure (specific)	50 - 100 bar
Residence time	< 6 min
Injection speed	Slow; Profile for constant melt flow front

Shrinkage²

	HTC, unfilled
Shrinkage, 24 h (ISO 294-4)	0.3 - 0.6 %

² Shrinkage is not a pure material property, but is influenced by fillers, the component geometry, its wall thickness and the position and size of the gate. Processing parameters, such as mold wall and melt temperature, also play a decisive role. Please also refer to the separate guide on shrinkage.

MOCOM Compounds GmbH & Co. KG
Mühlenhagen 35 | 20539 Hamburg
T +49 40 78105-720 | sales@mocom.eu
T +49 40 78105-710 | technical@mocom.eu
www.mocom.eu

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations.
NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.

MOCOM_0422